

XYSIL® 300**Hydrophilic Fumed Silica****TECHNIQUE DATA SHEET**

XYSIL® 300 is a hydrophilic Fumed Silica with a specific surface area of 300m²/g, and it is synthetic, hydrophilic, amorphous silica, produced via flame hydrolysis.

Physico-chemical Data

Properties	Units	Typical Value	Standardization
Specific surface area (BET)	m ² /g	300±25	GB/T10722
pH-value (in 4% dispersion)		3.8-4.5	GB/T1717
Loss on drying, ex works(2h @ 105°C)	wt%	<1.5	GB/T5211.3
Loss on ignition(2h @ 1000, based on material dried for 2h @ 105°C)	wt%	<2.5	GB/T20020
Sieve residue (45µm)	%	<0.05	GB/T5211.14
SiO ₂ content (based on the substance heated at 1000°C for 2 h)	wt%	>99.8	GB/T20020
Tamped density (based on material dried for 2h @ 105°C)	g/L	25~60	GB/T5211.4
Carbon content (based on material dried for 2h @ 105°C)	wt%	<0.2	GB/T20020

At time of packaging.

Applications and Properties

Application:

- ✧ HTV Silicone Rubber, Liquid Silicone Rubber
- ✧ Paints and Coatings, Ink, Pigment
- ✧ Unsaturated polyester resins
- ✧ Adhesive & Sealant

Functions:

- ✧ Rheology and thixotropy Control
- ✧ Used as anti-settling, thickening, anti-sagging agent
- ✧ Free Flow and Suspension
- ✧ Reinforcement
- ✧ Excellent transparency

Packing and Storage

XYSIL® 300 is packaged in multiple layer kraft paper 10kg bags on pallet, and should be stored in the original packaging in dry storage areas for protecting the material from volatile substance.

Transportation:

Sea Transportation
 20'GP: 1800KG, 10 pallets, 180KG/pallet.
 40'GP: 3600KG, 20 pallets, 180KG/pallet.
 40'HQ: 4000KG, 20 pallets, 200KG/pallet.
 Road Transportation: by requirement

This information is supplied on basis of our best knowledge, as a convenience and for information purposes only. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights.

Henan Xunyu Chemical Co.,Ltd

Add: No.18, Shangwu Waihuan Road, Zhengdong New Dis, Zhengzhou City, Henan Province, P.R. China

Tel: +86 371 69176282 Fax: +86 371 69176283

Email: info@xunyuchem.com; technique@xunyuchem.com

Website: www.xunyuchem.com